



CONSERVATION REPORT CR 604.06.24

CLIENT Inner Temple Library

CONTACT DETAILS Robert Hodgson <RHodgson@innertemple.org.uk>

ITEM / REFERENCE Fitzherbert's Abridgement

REPORT DATE 5<sup>th</sup> June 2024

# **DESCRIPTION**

Illuminated vellum bound manuscript of Fitzherbert's Digest. The vellum cover is not contemporary to the text block; the text block appears to be early 14<sup>th</sup> century, whereas the cover is later but still medieval. The text block, perhaps, originally had a different cover. Paper endpapers were also added at the same time as the new cover.



Image I – Front cover

(material and make-up)



Image 2 - Spine

Dimensions (L x B x H, mm)  $137 \times 108 \times 45$ 

Binding type Laced on limp vellum

Gatherings 16, with 5 bifolia per gathering of vellum

Text/media The main body of the text is written in iron gall ink. Illuminations

have been added to nearly all pages. All titles have gold leaf added to the first letter. From the date of the manuscript, the pigments used are likely to be gold leaf, Verdigris, vermillion or red lead, lapis lazuli or azurite, white lead and ochre. The volume is

paginated.

Collation Pastedown/endpaper bifolio tipped to textblock – I bifolio of

vellum – 16 gatherings – 1 extra vellum bifolio – endpapers/

pastedown (2 bifolios) tipped to text block.

l NCS consultancy is provided through Conservation Ltd, a company registered in England &Wales no. 6659286 VAT reg. 981-6962-69. NCS membership is provided through a not-for-profit company limited by guarantee, registered in England & Wales no. 7707608. Both companies are registered at 21 Albemarle St, Mayfair, W1S 4BS.



### Inner Temple Library/ Fitzherbert's Abridgement

Endpapers Handmade laid paper – perhaps added at the same time as the

limp vellum cover.

Sewing flexible sewing on double cord supports. Alum tawed thong

supports woven through the original cord supports. These thongs

form the cover attachment.

Covering material Vellum

Housing Bespoke archival clamshell box

#### CONDITION

Text block

The overall condition of the text block is fair. There is some staining at the head of the text block in the final gathering. Overall surface dirt present, particularly on the original vellum endpapers of the volume, which are quite dark with ingrained particulate dirt, and also the text block edges.

Pages 90, 91 and 92 are all slightly distorted, with creases present - possibly through exposure to high humidity, heat or both. The vellum also feels slightly stiffer and less flexible. This is the case also for the final vellum endpaper.

The spine of the text block is fully accessible from the front of the volume due to the alum tawed thongs having broken at the joint. The backs of the gatherings have a thick layer of very discoloured adhesive (most likely from their previous binding) and there are heavy deposits of dirt.

The profile of the spine has also become concave, meaning the fore-edge juts out beyond the edges of the cover.

Media The iron gall ink manuscript text is stable throughout.

Pigments: The pigments are generally stable. There is burn through of the Verdigris in every instance that it is applied due to the copper content. Of all the colours used in the illuminations, the gold seems to have suffered the worst with areas having flaked off. Under magnification, it appears stable and so the

damage presumed to be historic.

Endpapers The additional paper endpapers and pastedown are in fair

condition. At the front it has detached where it was tipped to the text block, has surface dirt and is slightly discoloured. It is also starting to split along the fold and there is evidence that it was

once sewn.

# Inner Temple Library/ Fitzherbert's Abridgement

At the back there are two free end leaves and then two pastedowns. The end leaves and top layer of pastedown have signs of insect damage. The pastedowns also have a vertical split that runs most of the way up.

Sewing

All three of the original cord sewing supports have split halfway across the width of the spine. The sewing at the kettle at this point, at both head and tail, has broken too. Within the text block the sewing still seems strong, apart from within the 9<sup>th</sup> gathering, which is loose.

**Board** attachment

The alum tawed thongs that were the primary cover attachment have split at the front and the additional paper endpapers have detached from the rest of the text block. The cover is now only attached by the laced thongs at the back and sewing thread which goes around the original supports and through the fold of the end leaves.

Covering

The covering, although in poor condition, does still offer some protection to the text block. There is a small area of the front fore edge, towards the bottom, that has been eaten by a pest. The back of the cover has a large area of planar distortion, which is what has caused the split in the pastedown.

The turn in at the tail has worn away in areas.

Due to ingrained particulate dirt, the cover has an overall grubby appearance.

Housing Good.

Overall condition rating Poor








Image 3 – Split sewing supports

Image 4 – Split text block








Image 7 – Loose gathering



Image 8 – Creased, discoloured vellum endpaper

# TESTS AND (RESULTS)

No tests were carried out as part of this report.

# **RECOMMENDED TREATMENT**

Option 2		
	Treatment step	Materials
1.	Surface clean throughout	Chemical sponge, soft brush
2.	Remove text block fully from cover  Clean adhesive off spine and remove original sewing	Wheat starch paste poultice (applied through goldbeaters' skin)
3. 4.	Repair folded area of front paper endpaper  Resew text block on new thongs  Lace cover back on OR if the cover no longer fits add a new flav paper cover	Japanese paper 12gsm, wheat paste  White tawed goatskin, wheat paste, linen thread
	fits add a new flax paper cover	Flax paper

# TREATMENT DESCRIPTION/OBSERVATION

To be completed following treatment